

Coverage Table

Coatings or Membranes

(Theoretical) Coverage's for Coatings or Membranes

Thickness of Coating\Membrane Applied (1000 mils = 1 in.)	Coverage per U.S. Gallon 100% Solid System
1/4" = 250.000 mils	6.4 sq. ft.
3/16" = 187.500 mils	8.5 sq. ft.
1/8" = 125.000 mils	12.8 sq. ft.
1/8" = 100.000 mils	16.0 sq. ft.
1/16" = 62.500 mils	25.7 sq. ft.
1/16" = 50.000 mils	32.1 sq. ft.
1/32" = 31.250 mils	51.3 sq. ft.
1/32" = 20.000 mils	80.2 sq. ft.
1/64" = 15.625 mils	102.7 sq. ft.
1/64" = 10.000 mils	160.4 sq. ft.
1/64" = 5.000 mils	320.8 sq. ft.
1/64" = 1.000 mils	1604.2 sq. ft.

Note: If a coating contains a solvent which evaporates, the thickness of the coating will be reduced by the same percentage as the solvent loss.